



**ZHEJIANG GANGLONG NEW MATERIAL CO., LTD.**  
MAQIAO WARP KNITTING SCIENCE & TECHNOLOGY INDUSTRIAL ZONE  
HAINING ZHEJIANG CHINA  
TEL: 0086-573-7768287 FAX: 0086-573-7760999

### TECHNICAL DATA

Description of commodity: GLP048-1/ GLP071 Backlit PET 320gsm			
ITEM	DATA	UNIT	TEST METHOD
Thickness Micron	29		
Fabric	NO		DIN EN ISO2060
Total weight	320	g/sq.m	DIN53352 BS3424 method5A
Weight of PET	175	g/sq.m	DIN53352 BS3424 method5B
Weight of PVC	145	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp: 1180	N/5cm	DIN53354 BS3424 method6A
	Weft: 1030		
Tearing strength	Warp: 60	N	DIN53356 BS3424 method 7A
	Weft: 50		
Adhesion	60	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	-20 -----+70	°C	DIN 53372 BS3424 method10
Flame retardancy	As requested.		
Standard width:	1.80m,2.00m,2.20m,2.50m,2.80m and 3.20m		
Printer type:	Solvent / Eco-solvent / UV printers.		

The indexes above are on average, so there will be  $\pm 5\%$  tolerance for actual material.