

MACal® Glass Decor 500

PRODUCT DESCRIPTION

MACal Glass Decor 500 series are polymeric translucent vinyls coated with a long-life durable, highly cohesive acrylic pressure-sensitive adhesive. This is protected with a high quality plain or a bubble free (BF) liner.

Face material:

75 µm matt polymeric translucent stabilized vinyl film, cadmium-free.

Adhesive:

Plain: High quality acrylic solvent based adhesive, very cohesive and extremely durable.

BE: Micro-embossed, repositionable, clear solvent based acrylic adhesive.

Liner:

Plain: Highly stable 135 gsm white kraft paper printed with red backprinting.

Bubble Free (BF): Highly stable 145 gsm white micro-embossed PE coated paper with a blue backprinting.

TYPICAL USE

Windows decoration with a frosted or sandblasted effect. Suitable for outdoor and indoor applications.

PROCESSING

Screen process

MACal Glass Decor 500 series can be screen printed. Contact screen ink supplier for advice on suitable inks.

Plotters

Clean, quick, trouble-free cutting with most plotters. Adjustment of the cutting depth is important : if the cut is too deep this could result in the paper splitting and coming away with the adhesive when the vinyl is transferred to Application Tape. It is not recommended to plotter cut small letters with the BF version.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

APPLICATION METHOD

Application of pre-spaced letters, logos and decals made from MACal Glass Decor 500 is made easier using MACtransfer Application Tape.

For an uniform appearance, GlassDecor 500 plain is applied by the wet method whereas the BF version should be applied dry.

SOLVENT AND CHEMICAL RESISTANCE

Resistant to most oils and grease, fuel, aliphatic solvents, weak acids, salts and alkalis.

PHYSICAL PROPERTIES (TYPICAL VALUES)

Face Material Data, 23°C	Average values	Test method
Tensile strength (N/15mm)	> 28	DIN ISO 527-3
Elongation at break (%)	> 150	

Thickness	Plain	BF	
Face film + adhesive (µm)	105	105	ISO 534

Adhesive data, 23°C (N/25 mm)

Peel 180° on Stainless Steel

	20 minutes	24 hours	1 week	
	14	17	19	FTM 1

Dimensional stability

Shrinkage (48 hours at 70°C applied on aluminium)	Max. 0.3 mm	FTM 14
---	-------------	--------

Temperature ranges

Application temperature	+10 to 40°C
Service temperature range of use	- 40°C to + 90°C

Flammability

Sample mounted on aluminium	Self-extinguishing	ISO 3795
-----------------------------	--------------------	----------

EXPECTED DURABILITY*

Central Europe Zone 1

The expected vertical outdoor durability of the unprocessed product in central Europe (Zone 1) is up to 5 years. This information is based on successful real life experience and artificial aging according to ISO4892-3.

Note: Exposure to severe temperatures and ultraviolet light, as well as conditions in southern European countries, and also in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude, horizontal and south-facing exposure.

Important notice Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

Disclaimer and warranty Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.