

## JT 8300 WM-RT Dot Floors

### PRODUCT DESCRIPTION

Monomeric calendered self-adhesive floor graphic print media with dotted adhesive.

#### Face material:

200 µm white matt PVC

#### Adhesive:

Emulsion acrylic removable transparent dotted.

#### Liner:

Clay coated 120 g/sqm.

### TYPICAL USE

Short-term indoor promotional graphics on flat smooth floor surfaces.

### PROCESSING

Especially designed for solvent based, eco-solvent, mild solvent, Latex and UV\* inkjet printing on wide-format printing equipment.

JT 8300 WM-RT Dot Floors should not be laminated.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.

Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: [www.mactacgraphics.eu](http://www.mactacgraphics.eu). For further information on printing, application and removal, please refer to "TB 5.1 Application of Mactac JT 8300 Dot Floors".

\*Not compatible with UV-Gel inks

### SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

### APPLICATION METHOD

Mactac Digital media must be applied and used following the instructions in "TB 5.1 Application of Mactac JT 8300 Dot Floors" available from the resource section at [www.mactacgraphics.eu](http://www.mactacgraphics.eu).

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

### PHYSICAL PROPERTIES (TYPICAL VALUES)

Adhesive data, 23°C (N/25 mm)	Average values	Test method
Quick tack on glass JT 8300 WM- RT Dot Floors	4	FTM 9
Peel 24 hours on glass JT 8300 WM- RT Dot Floors	2	FTM 1

#### Dimensional stability

Shrinkage (48 hours at 70°C applied on aluminium)	Max. 1.0 mm	FTM 14
Shrinkage on liner (72 hours at 60°C)	Max. 2.3 mm	Internal method

#### Temperature ranges

Minimum application temperature	+ 10°C
Service temperature range of use	- 20°C to + 70°C

#### Certifications

Fire certification	Bfl-s1	EN13501-1
Anti-slip certification unprinted and printed*	PTV 36+ (low slip potential)	EN13036-4

\* For more information on printed anti-slip certification refer to "TB 5.1. Application of Mactac JT 8300 Dot Floors".

### EXPECTED DURABILITY\*

Central Europe Zone 1

Unprocessed	3 months	ISO 4892-2.
Printed and applied	1 month	ISO 4892-2.

\*For more information, refer to Technical Bulletin 7.5: "Outdoor Durability of combined MACTac print media and laminates".

Note: Exposure to heavy cleaning performed with brushes, chemicals and machines will affect the durability of the product and probably cause faster degradation of the inks. Always test the product to ensure end-use performance

#### DISCLAIMER

All Mactac statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Mactac products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. All Mactac's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.